

Bauder Bitumen 100/25

Technical data sheet

| | | |
|----------------|--|--|
| Method of use: | Hot melt bitumen composition for processing for example roofing membranes with pouring and rolling method | |
| | | |
| Article number | 7998 0000 | |

| | |
|---|-------------------------------|
| Delivery form | 30 kg in foil |
| Specific weight | Approx. 950 kg/m ³ |
| Processing temperatur | Approx. 180°C |
| Basis | Oxidbitumen |
| Needle penetration to DIN EN 1426 | 20 until 30 1/10mm |
| Breaking point (Frasß) to DIN EN 12593 | ≤ -10°C |
| Softening point (ring & ball method) to DIN EN 1427 | ≥ 95°C |
| Building material class DIN 4102-1 | B2 |

Hot bitumen for adhering roofing membranes, respectively BauderKOMPAKT.
 The bitumen blocks will be liquified by heating in a suitable bitumen cooker.
 Then the bitumen will be used on a dry and primer coated concrete base and the roofing membrane will be rolled into the liquid bitumen.