

# Bauder Burkolit V

## Technical Data Sheet

Type of application:	<b>Bituminous primer on solvent basis (not to be used indoors)</b>
	<b>For cold application by rolling, coating and spraying</b>
	<b>According to DIN 18195 - 2</b>
Article number	<b>7504 0000</b>

Delivery form	Hobbock 30 l
Suitability for storage	6 months at + 5°C to + 60°C in closed package
Minimum working temperature	+ 5°C
Basis	Solvent-based Bitumen
Consistency	Liquid
Bitumen content	approx. 30 weight-%
Product category according CEPE list	Group „g“
Allowed content of VOC according CEPE list	350 g/l
Max. content VOC in product	350 g/l
Drying time until dust-dry	approx. 3 hours
Consumption	approx. 300 g/m <sup>2</sup>
Giscode	BBP 30

Bituminous primer to improve the adhesion of bitumen membranes.

Bauder Burkolit V is applied by rolling, spraying or coating on full surface. The subsurface must be sufficiently dry and frost-free (+5°C surface of the underground).

Not to be used for interiors or e.g. building pits because it contains solvent.